

**PRODUCT DESCRIPTION**

LOCTITE® 5061 is a pre-applied, noncuring, non-toxic aqueous based thread sealant with good high temperature and solvent resistance. The coating is dry-to-the touch and ready for immediate use.

**TYPICAL APPLICATIONS**

Sealing threaded components such as pipe couplings and fittings, with either parallel or tapered threads, against gases, aqueous and non-aqueous fluids up to a temperature of 150°C. Particularly suitable in situations where threaded assemblies are required to be ready for immediate use in a high volume production environment where it may not be convenient to use a liquid sealant. LOCTITE® 5061 can be used to seal effectively on a wide variety of substrates including metals and plastics. The sealing of flat faces can also be achieved with this product.

**PROPERTIES OF DRY MATERIAL**

All properties described below refer to the dry pre-applied coating on parts as seen by end users.

Pre-applied (Dry film) coating

**Typical Value**

Chemical Type Polyacrylate Aqueous Emulsion Base  
 Appearance Soft dry light blue pre-applied film

**PERFORMANCE OF PRE-APPLIED MATERIAL**

**Pressure Tests on Nut & Bolt Assemblies**

Sealing ability of 5061 on nut and bolt assemblies was tested under pressure at room temperature and after solvent ageing. The pressure rig allows testing of 5 assemblies simultaneously in accordance to MIL-S-46163A.

**Burst pressure at room temperature**

Pressure increased gradually to 16 bar and then held constant for 1 minute.

Test Procedure: MIL-S-46163A Pressure rig (modified)  
 Test Specimens: M10 Nuts & Bolts

Substrates	Pressure (Bar)	Quantity Tested	Result
Black Oxide Bolt Mild Steel Nut	16	15	No Leaks
Zn Dichromate	16	15	No Leaks
Zn Phosphate	16	15	No Leaks
Stainless Steel	16	15	No Leaks

**Torque Tension Ratio - K Value (Lubricity)**

The torque tension ratio is a measure of the relationship between the torque input in an assembly and the resulting tension generated in the fastener. It is dependant on the substrates and geometry of the test pieces. The values obtained in any one test are specific and relate only to the conditions at the time of testing. It is therefore a comparative rather than an absolute measure of lubricity.

Test Specimens: M10 Nuts & Bolts  
 Applied Torque: 40 Nm

Substrates	K Values	
	As received	5061
Black Oxide Bolts Mild Steel Nuts	0.22 - 0.38	0.16 - 0.28
Zn Dichromate	0.22 - 0.34	0.17 - 0.25
Stainless Steel	0.30 - 0.46	0.23 - 0.39

**TYPICAL ENVIRONMENTAL RESISTANCE**

Test Procedure: MIL-S-46163A Pressure rig ( modified)  
 Substrates: M10 Black Oxide Bolts & Mild Steel Nuts

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested at 22°C

Solvent	Temp	Press.	100hr	500hr	1000hr
Water	90°C	4 bar	No leaks	No leaks	No leaks
Motor Oil	150°C	4 bar	No leaks	No leaks	No leaks

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidising materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).**

**Directions for use**

The product is a one component system consisting of an aqueous based liquid emulsion applied to fittings and fasteners and then dried. This can take place at an intermediate converter company or be done by the end user. Guidelines on recommended processing and drying conditions are available to converter companies through the local Technical Service Centre. The dry coated fitting/fastener is ready for immediate use and can be assembled to its mating threaded component at any time within its on-part shelf life period. For best performance the mating surface should be clean and free of grease. Product is normally pre-applied to the threaded component in sufficient quantity to fill all engaged threads by agreement between the converter and the end user. This

product performs best in thin bond gaps, (0.05mm). Very large thread sizes may create large gaps which will affect sealing performance and function should be verified.

### Storage

Coated fasteners shall be ideally stored in a cool, dry location at a temperature between 8°C - 21°C (46°F - 70°F). The onpart shelf-life period of a coated component is 24 months based upon date of application of coating. For further specific shelf-life information, contact your local Technical Service Centre.

### Data Ranges

The data contained herein may be reported as a typical value and/or range (based on the mean value  $\pm 2$  standard deviations). Values are based on actual test data and are verified on a periodic basis

### Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.